

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	CLASS	LIGHT ISO 105-B02	WASHING 40°C ISO 105-C01			WATER ISO 105-E01			SEA WATER ISO 105-E02			ACID PERSPIRATION pH 5.5 ISO 105-E04			ALKALINE PERSPIRATION pH 8.0 ISO 105-E04			CHLORINATED WATER ISO 105-E03		
			S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	50mg/l	100mg/l	
		C.C																	C.C	C.C
0028 BIANCO	class 1	3-4	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	3-4	3
0086 AVORIO	class 1	>5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	4	3-4
2160 INCAS	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	3
4073 VENERE	class 2	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5
6005 TURCHESE	class 2	3	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2	2
6266 BAIA	class 2	3	4-5	5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	3	2
7110 IRELAND	class 2	4	4	4-5	4-5	3-4	3-4	4-5	3	3-4	4	3-4	3-4	4-5	3	3-4	4-5	4	3-4	
8101 SEPPIA	class 2	>5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	2-3	
9154 TITANIUM	class 2	>5	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3
NEONS																				
3015 ROSA SHOCKING	class 2	1-2	4	4	4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	3-4	4	3-4	3-4	4	4	1	1
3099 DAFNE	class 2	1	5	5	5	3-4	3-4	4	3-4	3-4	4	3-4	3-4	4	3-4	3-4	4	4	2	1

C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.Pl: Staining on Polyester.

Testing procedure OEKO-TEX® STANDARD 100 Class 1 and Class 2, please refer to www.oeko-tex.com for more information.

• Colour dyed with a particular fluoro dyestuff that might create a 'blue stains' effect in conditions of high humidity and temperature. This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumble dry or hang dry.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		