

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	CLASS	LIGHT ISO 105-B02	WASHING 40°C ISO 105-C01			WATER ISO 105-E01			SEA WATER ISO 105-E02			ACID PERSPIRATION pH 5.5 ISO 105-E04			ALKALINE PERSPIRATION pH 8.0 ISO 105-E04			CHLORINATED WATER ISO 105-E03	
			S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	S.Co	S.Pa	S.Pl	50mg/l	100mg/l
		C.C																C.C	C.C
4209 COSMOPOLITAN	class 1	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2
4243 SHANGHAI	class 1	5	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	2-3	1
5716 PURPLE	class 2	3-4	4-4	3-4	4	4	3-4	4	4	3-4	4	4	3-4	4	4	3-4	4	1-2	1-2
6007 BLU SCURO	class 1	> 5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4
60081 TENERIFE	class 2	> 5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	1-2
60108 BLUE REBEL	class 2	5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	2-3	2
7863 JADE	class 2	3-4	3-4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	3-4	3
8165 DATTERO	class 2	> 5	4-5	4-5	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4	2-3
9040 NERO	class 2	> 5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	4-5	4	4-5	3-4	3
NEONS																			
1094 SIRIO	class 2	1-2	4	4	4	3	3	4	3	3	3-4	3	3	3-4	3	3	3-4	1	1
30009 INFLUENCER	class 2	1-2	4-5	4-5	4-5	4	4	4	3-4	3-4	3-4	4	4	4	4	4	4	1-2	1

- C.C: Colour Change.
- S.Co: Staining on Cotton.
- S.Pa: Staining on Nylon.
- S.Pl: Staining on Polyester.

Testing procedure OEKO-TEX® STANDARD 100 Class 1 and Class 2, please refer to www.oeko-tex.com for more information.

- Colour dyed with a particular fluoro dyestuff that might create a 'blue stains' effect in conditions of high humidity and temperature. This effect can be eliminated: machine wash the garment with soap at 30°C, delicate tumble dry or hang dry.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		