

COLOUR FASTNESS

Combination of colours is not recommended when the fastness values are lower than 4-5. When splicing colours with White we also recommend using a complimenting Polyester base.

COLOUR	WASHING 40 °C AS2001.4.15				WATER AS2001.4-E01				PERSPIRATION AS2001.4-E04				RUBBING AS2001.4.3		LIGHT AS2001.4.21
	S.Co	S.Pa	S.Pl	C.C	S.Co	S.Pa	S.Pl	C.C	S.Co	S.Pa	S.Pl	C.C	Dry	Wet	C.C
WHITE	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA	NA

- C.C: Colour Change.
S.Co: Staining on Cotton.
S.Pa: Staining on Nylon.
S.Pl: Staining on Polyester.

COLOUR FASTNESS ASSESSMENT VALUES			
LIGHT	ASSESSMENTS	OTHER TESTS	ASSESSMENTS
1	Very Weak	1	Weak
2	Weak	2	Limited
3	Moderate	3	Fair
4	Fair	4	Good
5	Good	5	Very Good
6	Very Good		
7	Optimal		
8	Exceptional		

SUBLIMATION TEST RESULTS	
LENGTH %	3%
WIDTH%	2.5%

Sublimation bases can react differently from machine to machine. Please ensure you test each fabric as a variation may occur due to machine settings and paper variation. Recommended sublimation procedure:

- 40 seconds
- 195-205 degrees
- No higher than 205

NOTE: 3-4% Shrinkage is deemed acceptable depending on the fabric type and knit construction.